


# FLORIDA NATURAL EXPOSURE - 1 YEAR



**Sample nr. 136**

**Base:** PROTEK POWDER  
**Decoration:** PROTEK FILM 9061/401  
**Exposure beginning:** 10/04/01  
**End of exposure:** 10/04/02  
**Thickness:** 61 microns

**Gloss Level at the beginning:** 18,4  
**Gloss Level at the end:** 17

**REMAINING GLOSS: 92%**



**Sample nr. 207**

**Base:** **NON PROTEK POWDER**  
**Decoration:** PROTEK FILM 9061/401  
**Exposure beginning:** 10/04/01  
**End of exposure:** 10/04/02  
**Thickness:** 67 microns

**Gloss Level at the beginning:** 21,6  
**Gloss Level at the end:** 5,9

**REMAINING GLOSS: 27%**